

IN THE CLAIMS:

1. (cancelled)

2. (cancelled)

3. (original) A two-component developer for use in electrographic printing comprising substantially spherical toner particles and substantially spherical magnetic carrier particles, the carrier particles having a dielectric constant ϵ_c of at least about 6, the toner particles having a radius R_T and the carrier particles having a radius R_C , wherein R_C is between about $1.5R_T$ and about $10R_T$.

4. (original) The developer of claim ¹~~3~~, wherein R_C is between about $2R_T$ and about $5R_T$.

5. (original) The developer of claim ¹~~3~~, wherein the carrier particles have a dielectric constant ϵ_c greater than about 10.

6. (original) The developer of claim ³~~5~~, wherein R_C is between about $2R_T$ and about $5R_T$.

7. (original) The developer of claim ¹~~5~~, wherein the carrier particles have a dielectric constant ϵ_c greater than about 100.

8. (original) The developer of claim ⁵~~7~~, wherein R_C is between about $2R_T$ to about $5R_T$.

9. (original) The developer of claim ¹~~7~~, wherein the carrier particles have a dielectric constant ϵ_c greater than about 298.

10. (original) The developer of claim ⁷~~9~~, wherein R_C is between about $2R_T$ to about $5R_T$.

¹⁷
~~11~~. (currently amended) A method for producing electrographic images comprising the steps of:

(a) providing an electrographic printer comprising an imaging member, a toning shell located adjacent the imaging member and defining an external electric field of image development therebetween, and a two-component developer, comprising substantially spherical toner particles and substantially spherical magnetic carrier particles,

the carrier particles having a dielectric constant ϵ_c of at least about 6,

the toner particles having a radius R_T and the carrier particles having a radius R_C , wherein R_C is between about $1.5R_T$ and about $10R_T$; and

(b) causing developer to move through the external electric field, interacting with an electrostatic image carried on the imaging member.

¹⁸
~~12~~. (original) The method of claim ¹⁷~~11~~, wherein R_C is between about $2R_T$ and about $5R_T$.

¹⁹
~~13~~. (original) The method of claim ¹⁷~~11~~, wherein the carrier particles have a dielectric constant ϵ_c greater than about 10.

²⁰
~~14~~. (original) The method of claim ¹⁹~~13~~, wherein R_C is between about $2R_T$ and about $5R_T$.

²¹
~~15~~. (original) The method of claim ¹⁷~~11~~, wherein the carrier particles have a dielectric constant ϵ_c greater than about 100.

²²
~~16~~. (original) The method of claim ²¹~~15~~, wherein R_C is between about $2R_T$ to about $5R_T$.

²³
~~17~~. (original) The method of claim ¹⁷~~11~~, wherein the carrier particles have a dielectric constant ϵ_c greater than about 298.

A

²⁴
~~18~~. (original) The method of claim ²³~~17~~, wherein R_C is between about $2R_T$ to about $5R_T$.

²⁵
~~19~~. (original) The method of claim ¹⁷~~11~~, wherein the external electric field of image development is less than the electric field produced by a uniformly-charged toner particle of charge q and radius R_T .

⁹
~~20~~. (currently amended) The developer of claim ¹~~3~~ 4, the carrier particles having a size distribution according to the Schulz distribution with z greater than about 6.

¹⁰
~~21~~. (currently amended) The developer of claim ¹~~3~~ 4, the carrier particles having a size distribution according to the Schulz distribution with z greater than about 10.

¹¹
~~22~~. (currently amended) The developer of claim ¹~~3~~ 4, the carrier particles having a size distribution according to the Schulz distribution with z greater than about 50.

¹²
~~23~~. (currently amended) The developer of claim ¹~~3~~ 4, the carrier particles having a size distribution according to the Schulz distribution with z greater than about 100.

¹³
~~24~~. (currently amended) The developer of claim ¹~~3~~ 4, the toner particles having a size distribution according to the Schulz distribution with z greater than about 20.

¹⁴
~~25~~. (currently amended) The developer of claim ¹~~3~~ 4, the toner particles having a size distribution according to the Schulz distribution with z greater than about 30.

¹⁵
~~26~~. (currently amended) The developer of claim ¹~~3~~ 4, the toner particles having a size distribution according to the Schulz distribution with z greater than about 50.

¹⁶
~~27~~. (currently amended) The developer of claim ¹~~3~~ 4, the toner particles having a size distribution according to the Schulz distribution with z greater than about 100.